

**ENHANCEMENT OF THE SORTPION PROPERTIES OF FOAM RUBBER BY
INCORPORATING A SUITABLE ADSORBENT**

By

T. O. Kumanayaka

THIS THESIS WAS SUBMITTED TO THE
DEPARTEMNT OF CHEMICAL AND PROCESS ENGINEERING
OF THE UNIVERSITY OF MORATUWA
IN PARTIAL FULFILLMENT OF THE REQUIREMENT FOR THE DEGREE OF
MASTER OF SCIENCE



66 "07"
66 (043)

DEPARTMENT OF CHEMICAL AND PROCESS ENGINEERING
UNIVERSITY OF MORATUWA
MORATUWA
SRI LANKA

University of Moratuwa



87851


87851

FEBRUARY 2007

87851

DECLARATION

I certify that this thesis does not incorporate without acknowledgement any material previously submitted for a degree or diploma in any university and to the best of my knowledge and belief it does not contain any material previously published, written or orally communicated by another person except, where due reference is made in the text.


.....


T.O kumanayaka

04/8216



University of Moratuwa, Sri Lanka.
Electronic Theses & Dissertations
www.lib.mrt.ac.lk

Certified by


.....

(Dr. Shantha Walpolage)

Supervisor

ACKNOWLEDGMENT

From the beginning I would like to offer my grateful thanks to Dr. Shantha Walpolage, Senior lecture, Department of chemical and Process Engineering, University of Moratuwa, for his kind and patience, supervision and excellent guidance during the entire course of this project.

My grateful thank also goes to Prof. Ajith de Alwis Head of the Chemical & Process Engineering Department, Dr Jagath Premachandra, Senior Lecturer and all other lectures of the Department of Chemical & Process Engineering, University of Moratuwa, who helped and encouraged me in various ways to complete this project successfully .

Then I'm very much thankful to the Wonderlight Consumer Products (Pvt.) Ltd. and Beco link (Pvt.) Ltd. for supplying raw materials for the project.

I wish to thank Mr. M. A. Hemachandra, Miss. A. S. Wahalathanthri and Mr. M. G. S. K. De Silva and special thank goes to Mr. Janaka Madushanka for their support given me in various occasions during the project period.

I warmly remind my beloved parents and my husband Chamila Amaradiwakara for all the encouragement and the support given me as usual to success this project.

Finally I would like to thank my friends, especially Sashmial Dissanayaka, Poornima Jayasingha, Gayan Bandara & Chinthaka Narangoda who were with me and gave their kind co-operation through out this project.

CONTENTS

Acknowledgement	i
List of Tables	vi
List of figures	viii
Abbreviations	ix
Abstract	x

CHAPTER 1: INTRODUCTION

1.1 Natural rubber latex foam	01
1.2 Uses of Latex foam	01
1.3 Filler incorporation to latex foam	02
1.4 Objectives of the research	03

CHAPTER 2 : LITRATURE REVIEW

2.1 Polymer Latex	04
2.2 Natural Rubber latex	04
2.2.1 Composition of field latex	04
2.2.2 Preservation of natural rubber latex	05
2.2.3 Concentration of natural rubber latex	06
2.3 Manufacture of natural rubber (NR latex foam)	07
2.3.1 Manufacturing process of foam rubber	08
2.4 Foam Economies	20
2.5 Theoretical aspects of adsorption	21
2.5.1 Factors affecting adsorption	21
2.5.2 Adsorbents	22
2.6 Activated Carbon	22
2.6.1 Manufacture of activated carbon	23
2.6.2 Pore structure of activated carbon	25
2.6.3 Activated carbon structure and surface chemistry	26

2.6.4 Application of activated carbon	28
2.7 Zeolite	
2.7.1 Origin of zeolite	29
2.7.2 Structure of zeolite	29
2.7.3 Pore structure of zeolite	32
2.7.4 Applications of zeolite	33
2.8 Incorporation of adsorbent into natural rubber latex foam	34
2.9 Applications of modified NR foam	35
2.9.1 Applications in indoor air pollution	35
2.9.2 Steps to improve the indoor air quality	37
2.9.3 Modified NR foam applications in odour removing	37
2.9.4 Physical adsorption	38
 CHAPTER 3: METHODOLOGY	
3.1 Experimental design	39
3.2 Testing of adsorbents	40
3.2.1 Determination of pH	40
3.2.2. Determination of Avg. particle size	40
3.2.3 Determination of moisture content	40
3.3 Methods of dispersion preparation	41
3.3.1 Determination of the best preparation method	41
3.4 Preparation of adsorbent dispersion with maximum TSC. & Investigate the Dispersion properties	42
3.4.1 Preparation of dispersion with varying TSC %	42
3.4.2 Determination of dispersion properties	43
3.5 Determination of the best dispersions for making a stable latex compound	45
3.5.1 Preparation of latex compound	45
3.5.2 Determination of the properties of the basic latex compound	47
3.5.3 Selection of the best adsorbent dispersion for making a Stable latex compound	49

3.6 Determination of the effect of dosage of adsorbent for stable NR foam	50
3.6.1 Stability of the latex compound at partially foam stage	51
3.6.2 Chemical stability towards gelling agents	51
3.6.3 Structure analysis of foam with different dosage of adsorbent	51
3.7 Determination of physical properties	52
3.7.1 Tensile strength	52
3.7.2 Indentation hardness	53
3.7.3 Density and shrinkage percentage	53
3.7.4 Flame retardant property	53
3.8 Determination of sorption capacity of modified NR foam with adsorbents	54
3.8.1 Determination ammonia gas sorption capacity	54
3.8.2 Determination of CO ₂ sorption capacity	55
3.8.3 Determination of Acetone sorption capacity	55
 CHAPTER 4: RESULTS AND DISCUSSION	
4.1 Properties of selected adsorbents	56
4.2 Preparation of adsorbent dispersions	57
4.2.1 Selection of the best preparation for zeolite powder	57
4.2.2 Selection of the best preparation for activated powder	57
4.3 Preparations of adsorbent dispersions with maximum T.S.C	61
4.3.1 Properties of dispersions with varying T.S.C. %	61
4.4 Incorporation of adsorbent dispersions to NR latex compound	65
4.4.1 Properties of basic latex compound	65
4.4.2 Effect of adsorbent dispersions for the stability of latex compound	65
4.5 Effect of dosage of adsorbent for preparing stable foam of NR latex	69
4.5.1 Determination of stability of latex foam varying zeolite dosage at Partial foamed stage	69
4.5.2 Chemical stability of latex compound with varying zeolite dosage	72
4.5.3 Structure analysis of foam with varying zeolite dosage	75
4.6 Physical properties of foam samples produced by batch scale process	81

4.7 Measurement of sorption property of modified latex foam	91
4.7.1 Ammonia gas sorption of foam with adsorbents	86
4.7.2 Carbon dioxide sorption of foam with adsorbents	96
4.7.3 Acetone sorption of foam with adsorbents	99
 CHAPTER 5: CONCLUSIOS AND RECCOMENDATIONS	
5.1 Conclusions	102
5.2 Suggestions for further studies	103
 REFERENCES	104



University of Moratuwa, Sri Lanka.
Electronic Theses & Dissertations
www.lib.mrt.ac.lk

LIST OF TABLES

<i>Table 2.1</i> A typical composition of field latex	05
<i>Table 2.2</i> Composition of Centrifuged latex concentrates	07
<i>Table 2.3</i> Effect of filler on some foam properties	20
<i>Table 2.4</i> Chemical analysis of major elements in zeolite	29
<i>Table 3.1</i> Formula for zeolite dispersions	42
<i>Table 3.2</i> Formula for activated carbon dispersions	43
<i>Table 3.3</i> Formula for latex compound with varying zeolite dosage	50
<i>Table 3.4</i> Formula for latex compound with varying activated carbon dosage	50
<i>Table 4.1</i> Properties of selected adsorbents	56
<i>Table 4.2</i> Properties of Zeolite dispersions	57
<i>Table 4.3</i> Properties of Activated carbons dispersions	58
<i>Table 4.4</i> Properties of zeolite dispersions series	61
<i>Table 4.5</i> Properties of activated carbon dispersions series	61
<i>Table 4.6</i> Properties of compounded latex	65
<i>Table 4.7</i> Results of coagulum formation test with 1% adsorbent dosage	65
<i>Table 4.8</i> Results M.S.T of latex compounds with 1% adsorbent dosage	65
<i>Table 4.9</i> Variation of chemical stability in latex compound with 1% adsorbent	65
<i>Table 4.10</i> Normalized foaming heights of latex compound at partially foamed stage for different dosages of zeolite	69
<i>Table 4.11</i> Normalized foaming heights of latex compounds at partially foamed stage for different dosages of activated carbon	70
<i>Table 4.12</i> Gel times of latex compounds series of zeolite	72
<i>Table 4.13</i> Gel times of latex compounds series of AC	73
<i>Table 4.14</i> Structure analysis of foam with zeolite adsorbent	75
<i>Table 4.15</i> Structure analysis of foam with AC adsorbent	79
<i>Table 4.16</i> Tensile strength of foam samples	82
<i>Table 4.17</i> Indentation hardness of foam samples	84
<i>Table 4.18</i> Density and shrinkage % of foam samples	86
<i>Table 4.19</i> Flame retardant property of foam samples	89

<i>Table 4.20</i> Ammonia gas sorption % of foam modified with zeolite	91
<i>Table 4.21</i> Ammonia gas sorption % of foam with 8% dosage of zeolite	92
<i>Table 4.22</i> Ammonia sorption capacity of foam with 85 dosage of zeolite	93
<i>Table 4.23</i> Ammonia sorption capacity of foam modified with AC	94
<i>Table 4.24</i> Minimum CO ₂ sorption % of foam with zeolite	96
<i>Table 4.25</i> Minimum CO ₂ sorption % of foam with AC	97
<i>Table 4.26</i> Acetone sorption % of foam with zeolite	99
<i>Table 4.27</i> Acetone sorption % of foam with AC	100



University of Moratuwa, Sri Lanka.
Electronic Theses & Dissertations
www.lib.mrt.ac.lk

LIST OF FIGURES

<i>Figure 2.1</i> Structure of Isoprene	04
<i>Figure 2.2</i> Schematic diagram of graphite lattice with a turbostratic structure	23
<i>Figure 2.3</i> Structure of carbonized and activated carbon	24
<i>Figure 2.4</i> Microscopic pore structure of activated carbon	25
<i>Figure 2.5</i> Functional groups on activated carbon surface	27
<i>Figure 2.6</i> Basic zeolite structure	30
<i>Figure 2.7</i> Crystallographic structure of zeolite	31
<i>Figure 2.8</i> Pore structure of zeolite	32
<i>Figure 3.1</i> Ball milled machine	41
<i>Figure 3.2</i> Mechanical stability tester	48
<i>Figure 3.5</i> Experimental design for ammonia sorption	54
<i>Figure 4.1</i> pH variations of dispersions	62
<i>Figure4.2</i> Particle size analysis of dispersions	63
<i>Figure4.3</i> Coagulum content of latex compound with different adsorbents	66
<i>Figure4.4</i> M.S.T of latex compound with different adsorbents	67
<i>Figure4.5</i> Gel time of latex compound with different adsorbents	68
<i>Figure4.6</i> Normalized foaming heights of latex compound with zeolite	70
<i>Figure4.7</i> Normalized foaming heights of latex compound with AC	71
<i>Figure4.8</i> Gel time of latex compound with zeolite	73
<i>Figure4.9</i> Gel time of latex compound with AC	74
<i>Figure4.10</i> Foam samples with zeolite	78
<i>Figure4.11</i> Foam samples with zeolite	80
<i>Figure4.12</i> Tensile strength of foam samples	83
<i>Figure4.13</i> Indentation hardness of foam samples	85
<i>Figure4.14</i> Density of foam samples	87
<i>Figure4.15</i> Shrinkage % of foam sample	88
<i>Figure4.16</i> Flammability of foam samples	90
<i>Figure4.17</i> Ammonia sorption of foam with zeolite	92
<i>Figure4.18</i> Saturation & re sorption of foams with zeolite	93
<i>Figure4.19</i> Ammonia sorption % of foams with AC	94

<i>Figure4.20</i> CO ₂ sorption % of foam with zeolite	97
<i>Figure4.21</i> CO ₂ sorption % of foam with AC	98
<i>Figure4.22</i> Acetone sorption of foam with zeolite	100
<i>Figure4.23</i> Acetone sorption of foam with AC	101

ABBREVIATIONS

TSC	Total solid content
MST	Mechanical stability time
AC	Activated carbon



University of Moratuwa, Sri Lanka.
Electronic Theses & Dissertations
www.lib.mrt.ac.lk

ABSTRACT

Natural rubber latex is a colloidal dispersion of cis 1,4-polyisoprene in an aqueous medium. Chemicals are added to NR latex mainly as dispersions, emulsions and solutions at the compounding stage of latex to enhance the processing characteristics and to achieve the desired properties of the final product. The addition of various chemicals into latex as one of the above method should be able to maintain the colloidal stability of the latex. The colloidal stability of the latex compound is governed by the particle size, physical nature, viscosity, pH and the stability of the dispersions.

In this study an attempt was made to enhance the sorption properties of NR latex foam by introducing a suitable adsorbent into the latex compound. There was an early attempt on incorporation of activated carbon into the natural rubber latex foam. From this investigation it was found instead of activated carbon zeolite mineral can be used as an adsorbent with minimizing the problems compared to activated carbon incorporation. Stable dispersion of 36 % zeolite can be prepared by mixing the zeolite with dispersing agent and water. The mechanical agitation in ten minutes is sufficient to prepare the zeolite dispersion with satisfying the basic requirements of a stable dispersion. According to the chemical and mechanical stability studies on the latex compound, it has revealed up to 8% (on dry weight) dosage of zeolite dispersion can be incorporated into latex compound without disturbing the fine, continuous cell structure of NR foam. The similar investigation was carried out with the activated carbon and compared with zeolite foam samples. Activated carbon dispersion prepared as 25 % stable dispersion and incorporated into NR foam up to 5% (on dry weight) dosage.

The results of the experiment reveals that NR latex foam with Zeolite has a significant sorption properties for ammonia and carbon dioxide gases compared to foam with activated carbon whereas organic matter sorption is higher in foams with Activated carbon adsorbent. This sorption property of foams with zeolite can be used to generate a pleasant indoor environment by reducing odour and pollutant gases.